



# EZY-PAK™ #125

## ARCTIC GRADE PACKING COMPOUND

### DESCRIPTION

**EZY-PAK #125** packing compound is specifically designed for use in severe arctic conditions. Formulated from synthetic binders, silicone based polymers, inert fillers and fibers, **EZY-PAK #125** will conform to any shape, preventing leaks and/or foreign materials from entering the valve cavity. Excellent water resistance allows use for steam applications.

- Nontoxic
- Color: Light Blue
- Nonhardening
- Synthetic Base
- Nonhazardous
- Water Resistant
- Pumpable
- Hydrocarbon Resistant

### APPLICATIONS

**EZY-PAK #125** is specifically designed to provide a flexible packing for applications such as oilfield valve and wellhead used in arctic conditions. Due to the synthetic base, **EZY-PAK #125** is particularly effective in hot water, brine, and aqueous solutions or steam services to 550°F (288°C).

**EZY-PAK #125** can be injected into any area requiring packing with a high-pressure lubricator. It is best pumped through an injection valve having a 1/8" or larger bore, but can be pumped through a giant button head fitting with more effort.

### SERVICE RECOMMENDATIONS

- Liquid Hydrocarbons
- Gaseous Hydrocarbons
- Aqueous Solutions
- Crude Distillates
- Crude Oil
- Brine
- Water
- Steam

### TEMPERATURE RANGE

-75°F (-60°C) to 750°F (400°C)

### PRODUCT CHARACTERISTICS

Appearance	Light blue, semi-plastic, fibrous mass
Penetration (ASTM D-217)	45 – 75
Density (lb/gal) Typical	12.6
Specific Gravity	1.5
Dropping Point (ASTM D-2265)	None
Oil Separation Wt. % (ASTM D-6184)	1.0 max.
Thickener	Polymers & Mineral Silicates
Flash Point (ASTM D-92)	> 500°F (260°C)

**Note: Not for use with oxygen or strong oxidizers.**

**For package types and part numbers contact [sales@jetlube.com](mailto:sales@jetlube.com).**

### LIMITED WARRANTY

For warranty information please visit [http://www.jetlube.com/pdf/Jet-Lube\\_Warranty.pdf](http://www.jetlube.com/pdf/Jet-Lube_Warranty.pdf)

You can also email us at [sales@jetlube.com](mailto:sales@jetlube.com) or write to the Sales Department at the address below.